


DAVID J HEFFER AND ASSOCIATES

Consulting Textile
Technologists

22 Hicks Street, Lara, Vic, 3212
Tel: (03) 5282 1337

djheffer@djha.com.au
www.djha.com.au

ABN. 87 710 470 062



LABORATORY REPORT

Date : 7 August 2024

Report Number: 248527C

Client: HOAD FABRICS PTY LTD
PO BOX 360
BLACKTOWN NSW 2148

Reference: Laura Gummerson

Sample: woven, Bayview

Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
warp	-	0	4	4
weft	-	0	4	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

A handwritten signature in black ink, appearing to read 'David J Heffer'. The signature is fluid and cursive, with a prominent 'D' and 'H'.

DAVID J HEFFER
DIRECTOR